

THOMSON

DELPHION

RESEARCH
[My Account](#) | [Products](#)

PRODUCTS
[Search: Quick Number](#) | [Boolean](#) | [Advanced](#)

INSIDE DELPHION

The Delphion Integrated View

Get Now: ☒ PDF | [More choices...](#)

Tools: Add to Work File: [Create new Wo](#)

VI w: [INPADOC](#) | Jump to: ☒ Go to: [Derwent...](#)
☒ Email

🔍 Title: **JP61128459A2: SEPARATOR FOR SEALED LEAD-ACID BATTERY**

🔍 Country: **JP Japan**

🔍 Kind: **A**

🔍 Inventor: **SHINODA SUSUMU;**

🔍 Assignee: **ABEKAWA SEISHI KK**
[News, Profiles, Stocks and More about this company](#)

🔍 Published / Filed: **1986-06-16 / 1984-11-28**

🔍 Application Number: **JP1984000249639**

🔍 IPC Code: **H01M 2/16;**

🔍 Priority Number: **1984-11-28 JP1984000249639**

🔍 Abstract:

PURPOSE: To reduce cost and increase liquid retention ability and absorbency by making a separator with the mixture of glass fibers having a mean diameter thicker than 5 μ m, acid resistant synthetic fibers to which hydrophobic treatment is conducted, and water-containing amorphous silica with a paper machine.

CONSTITUTION: A separator for sealed lead-acid battery is made with the mixture of 10~30wt% glass fibers having a mean diameter thicker than 5 μ m, 40~80wt% acid resistant synthetic fibers to which hydrophobic treatment is conducted and in which at least 10wt% beating synthetic fibers are contained, 10~40wt% water-containing amorphous silica with a paper machine. Therefore, cost is reduced by removing expensive fine glass fibers, and liquid retention ability and absorbency are increased by using thicker glass fibers to increase capillary action. Moreover, by using synthetic fibers to which hydrophobic treatment is conducted, dispersion of fibers and mechanical strength are increased. Therefore, battery performance is improved.

COPYRIGHT: (C)1986,JPO&Japio

🔍 INPADOC
 Legal Status: **None**

Get Now: [Family Legal Status Report](#)

🔍 Family: [Show 2 known family members](#)

🔍 Other Abstract Info: **DERABS C86-194389 DERC86-194389**

